

GENERAL FEATURES

- Environmentally friendly
- Wide operating temperature range
- Nano gel electrolyte and long Floating service Life
- Can be used at vertical or horizontal orientation
- High Power Density
- Low self discharge


APPLICATIONS

- Telecom Control Equipments
- UPS systems
- Communication Equipments
- Medical Equipments
- Emergency Power Systems
- Security Systems
- Cable TV
- Railway System



DIMENSIONS & WEIGHT

Length(mm)	350±1
Width(mm)	167±1
Height(mm)	178±1
Total Height(mm)	178±1
Weight(kg)	21.4±3%



COMPLIED STANDARDS

IEC 60896-21/22	JIS C8704
YD/T1360	BS6290 part4
GB/T 19638	UL 1989

TECHNICAL SPECIFICATIONS



Nominal Voltage		12V(6 cells per unit)
Design Floating Life @25°C		12 Years
Nominal Capacity @25°C(10 hour rate@7.00A,10.80V)		70Ah
Capacity @25°C	20 hour rate (3.75A,10.5V)	75.0Ah
	5 hour rate (12.3A,10.5V)	61.5Ah
	1 hour rate (44.7A,9.6V)	44.7Ah
Internal Resistance	Full Charged Battery@25°C	≤6.8mΩ
Ambient Temperature	Discharge	-30°C~60°C
	Charge	-30°C~60°C
	Storage	-30°C~60°C
Max.Discharge Current@25°C		700A(5s)
Capacity affected by Temperature (10 hr Capacity)	40°C	108%
	25°C	100%
	0°C	90%
	-15°C	70%
Self-Discharge@25°C per Month		3%
Charge (Constant Voltage) @25°C	Standby Use	Initial Charging Current Less than 17.5A Voltage 13.6-13.8V
	Cycle Use	Initial Charging Current Less than 17.5A Voltage 14.4-14.9V

BATTERY DISCHARGE TABEL

Discharge Constant Current per Cell (Amperes at 25°C)







F.V/Time	15min	30min	45min	1h	2h	3h	5h	6h	8h	10h	20h
1.60V	126.4	74.4	56.4	44.7	26.3	19.3	13.0	11.3	8.9	7.4	3.89
1.67V	119.4	70.5	54.2	43.3	25.4	18.7	12.8	11.1	8.8	7.2	3.85
1.70V	112.1	68.5	52.2	41.7	24.7	18.2	12.5	10.9	8.7	7.1	3.79
1.75V	105.0	65.5	49.9	40.0	24.1	17.8	12.3	10.7	8.5	7.1	3.75
1.80V	98.5	63.1	48.1	38.6	23.2	17.2	12.0	10.5	8.4	7.0	3.71

Discharge Constant Power per Cell (Watts at 25°C)

F.V/Time	15min	30min	45min	1h	2h	3h	5h	6h	8h	10h	20h
1.60V	241.6	147.8	107.0	85.7	49.8	36.9	25.1	21.9	17.4	14.4	7.7
1.67V	231.1	138.5	103.4	83.4	48.4	35.9	24.7	21.6	17.2	14.2	7.6
1.70V	215.4	135.5	100.1	80.5	47.3	35.1	24.4	21.3	17.0	14.1	7.5
1.75V	202.1	129.0	96.1	77.6	46.2	34.4	24.0	20.9	16.8	13.9	7.5
1.80V	189.7	123.8	92.9	75.0	44.7	33.4	23.5	20.6	16.6	13.9	7.4

Note The above data are average values, and can be obtained within 3 charge/discharge cycles. These are not minimum values. Cell and battery designs/specifications are subject to modification without notice. Contact MCA for the latest information.

PERFORMANCE CHARACTERISTICS



BATTERY CONSTRUCTION

Component	Positive plate	Negative plate	Container & Cover	Safety valve	Terminal	Separator	Electrolyte	Pillar seal
Features	Thick high Sn low Ca grid with special paste	Balanced Pb-Ca grid for improved recombination efficiency	ABS (UL94-V0 optional)	Flame Si-Rubbeand aging resistancer	Female Copper Insert M6(torque:4~6N.m)	Advanced AGM separator for high pressure cell design	Dilute high purity sulphuric acid	Two layers epoxy resin seal