

GENERAL FEATURES

- Environmentally friendly
- Wide operating temperature range
- Nano gel electrolyte and long Floating service Life
- Can be used at vertical or horizontal orientation
- High Power Density
- Low self discharge


APPLICATIONS

- Telecom Control Equipments
- UPS systems
- Communication Equipments
- Medical Equipments
- Emergency Power Systems
- Security Systems
- Cable TV
- Railway System



DIMENSIONS & WEIGHT

Length(mm)	532±1
Width(mm)	206±1
Height(mm)	215±1
Total Height(mm)	219±1
Weight(kg)	48.5±3%



COMPLIED STANDARDS

IEC 60896-21/22	JIS C8704
YD/T1360	BS6290 part4
GB/T 19638	UL 1989

TECHNICAL SPECIFICATIONS



Nominal Voltage		12V(6 cells per unit)
Design Floating Life @25°C		12 Years
Nominal Capacity @25°C (10 hour rate@16.00A,10.80V)		160Ah
Capacity @25°C	20 hour rate (8.56A,10.5V)	171.2Ah
	5 hour rate (28.2A,10.5V)	141.0Ah
	1 hour rate (102.1A,9.6V)	102.1Ah
Internal Resistance	Full Charged Battery@25°C	≤4.7mΩ
Ambient Temperature	Discharge	-30°C~60°C
	Charge	-30°C~60°C
	Storage	-30°C~60°C
Max.Discharge Current@25°C		1600A(5s)
Short Circuit Current (A)		3400
Capacity affected by Temperature (10 hr Capacity)	40°C	108%
	25°C	100%
	0°C	90%
	-15°C	70%
Self-Discharge@25°C per Month		3%
Charge (Constant Voltage) @25°C	Standby Use	Initial Charging Current Less than 32A Voltage 13.6-13.8V
	Cycle Use	Initial Charging Current Less than 32A Voltage 14.4-14.9V

BATTERY DISCHARGE TABLE

Discharge Constant Current per Cell (Amperes at 25°C)







F.V/Time	15min	30min	45min	1h	2h	3h	5h	6h	8h	10h	20h
1.60V	288.8	170.1	128.8	102.1	60.0	44.2	29.8	25.9	20.3	16.8	8.88
1.67V	272.8	161.1	123.8	99.0	58.1	42.7	29.3	25.4	20.2	16.5	8.80
1.70V	256.2	156.5	119.4	95.2	56.5	41.6	28.6	25.0	19.8	16.3	8.67
1.75V	240.0	149.6	114.1	91.4	55.0	40.6	28.2	24.5	19.5	16.2	8.56
1.80V	225.1	144.2	109.9	88.2	53.0	39.4	27.5	24.0	19.2	16.0	8.48

Discharge Constant Power per Cell (Watts at 25°C)

F.V/Time	15min	30min	45min	1h	2h	3h	5h	6h	8h	10h	20h
1.60V	552.2	337.8	244.6	195.8	113.8	84.3	57.4	50.1	39.7	32.8	17.5
1.67V	528.3	316.6	236.3	190.6	110.7	82.1	56.5	49.3	39.4	32.5	17.4
1.70V	492.3	309.8	228.8	184.0	108.2	80.2	55.7	48.6	38.9	32.2	17.2
1.75V	461.9	294.9	219.7	177.3	105.6	78.6	54.9	47.8	38.4	31.8	17.0
1.80V	433.6	282.9	212.3	171.5	102.1	76.3	53.8	47.0	37.9	31.7	16.9

Note The above data are average values, and can be obtained within 3 charge/discharge cycles. These are not minimum values. Cell and battery designs/specifications are subject to modification without notice. Contact **MCA** for the latest information.

PERFORMANCE CHARACTERISTICS



BATTERY CONSTRUCTION

Component	Positive plate	Negative plate	Container & Cover	Safety valve	Terminal	Separator	Electrolyte	Pillar seal
Features	Thick high Sn low Ca grid with special paste	Balanced Pb-Ca grid for improved recombination efficiency	ABS (UL94-V0 optional)	Flame Si-Rubbeand aging resistancer	Female Copper Insert M8(torque:7 ~9N.m)	Advanced AGM separator for high pressure cell design	Dilute high purity sulphuric acid with fumed Silica gel	Two layers epoxy resin seal